

RAW MATERIAL TECHNICAL SPECIFICATION**CALCINED CAOLIN – FLINT CLAY**

Chemical specification	
Al ₂ O ₃	42 % MIN
Fe ₂ O ₃	2 % MAX
H ₂ O	0,5 % MAX

Physical specification	
Size	on request
Bulk Density	2,45 g/ccm MIN

Application	casting industry, refractory industry, production of abrasives
--------------------	--

V. Jakomin - director