

tel.: +386 (0) 8 2053743
fax.: +386 (0) 5 9926075
E-mail: euromark@siol.net
VAT: SI53612426

RAW MATERIAL TECHNICAL SPECIFICATION**MULLITE**

Chemical specification	
Al ₂ O ₃	59 % MIN
Fe ₂ O ₃	1,35 % MAX
H ₂ O	0,5 % MAX

Physical specification	
Size	on request
Bulk Density	2,70 g/ccm MIN

Application	casting industry, refractory industry, production of abrasives
--------------------	--

V. Jakomin - director