

Vojkovo nabrežje 32, 6000 KOPER, Slovenija

tel.: +386 (0) 5 6250106, 6250107

fax.: +386 (0) 5 9926075

e-mail: euromark@siol.net

VAT: SI53612426

**RAW MATERIAL TECHNICAL SPECIFICATION****BAUXITE ROTARY KILN**

<b>Chemical specification</b>	
Al <sub>2</sub> O <sub>3</sub>	85 % MIN
Fe <sub>2</sub> O <sub>3</sub>	1.8 % MAX
H <sub>2</sub> O	0.5 % MAX

<b>Physical specification</b>	
Size	on request
Bulk density	3.25 g/ ccm MIN

<b>Application</b>	Casting industry , refractory industry, production of abrasives
--------------------	---

E . Peroša – director

Revision 1/19