

Vojkovo nabrežje 32, 6000 KOPER, Slovenija

 tel.: +386 (0) 5 6250106, 6250107
 fax.: +386 (0)5 9926075
 e-mail: euromark@siol.net
 VAT: SI53612426

RAW MATERIAL TECHNICAL SPECIFICATION
CHEMICAL BAUXITE

TECHNICAL SPECIFICATIONS	TYP. (%)		DISP. (p.p.)
Al ₂ O ₃	68	MIN	+/- 2.00
TiO ₂	1.5	MAX	+/- 0.30
Fe ₂ O ₃	3	MAX	+/- 0.50
CaO	3	MAX	+/- 0.30
MgO	9	MAX	+/- 1.00
K ₂ O	0.77	MAX	+/- 0.19
SiO ₂	9	MAX	+/- 1.00
Na ₂ O	1.8	MAX	+/- 0.20
MnO	0.25		+/- 0.10
P ₂ O ₅	0.15		+/-0.10
Cr	0.05		
Ni	0.03		
Cu	0.44		
Zn	0.07		
Sr	0.03		
Zr	0.01		
Ba	0.25		
Pb	0.02		
S	0.22		
As	0.0019		

E. Peroša director

Revision 1/21