

Vojkovo nabrežje 32, 6000 KOPER, Slovenija

tel.: +386 (0) 5 6250106, 6250107
fax.: +386 (0) 5 9926075
e-mail: euromark@siol.net
VAT: SI53612426**RAW MATERIAL TECHNICAL SPECIFICATION****SINTERED SPINEL**

Chemical specifications	
Al ₂ O ₃	74.00 % MAX
Fe ₂ O ₃	0.20 % MAX
Na ₂ O + K ₂ O	0.30 % MAX
SiO ₂	0.30 % MAX
MgO	20.05 % MIN
CaO	0.20 % MIN
B.D	3.20 gg/ccm MIN
Apparent porosity	5.00 % MAX

Physical specification	
Size	On request

Application	Casting industry , refractory industry, production of abrasives
--------------------	---

E. Peroša – director

Revision 1/19